

Biodegradable*
Recycled Content
Bleach Cleanable

Seating

Emerge 2178

Citrine
902

Cloud
911

Atmosphere
910

Featherstone
913

Clay
904

Parchment
901

Aloe
908

Cobalt
909

Graphite
914

Smoke
912

Terra Rose
903

Cerise
905

Emerald
907

Squid Ink
906

Evening
915

Emerge 2178

CLEAN IMPACT **TEXTILES**[®]

Specifications

Content	81% post-consumer recycled biodegradable* polyester 19% pre-consumer recycled biodegradable* polyester
Weight	12.4 ± 1.0 oz./lin. yd
Width	54" min. useable
Repeat	12" horizontal 18.25" vertical
Backing	none
Treatment	none

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup.

Bleach Cleanable - May be cleaned with a 10% bleach-to-water solution. Rinse well after cleaning. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Miscellaneous

- Application testing of this product is recommended.
- Colors may vary between dye lots.
- This is a directional fabric.

Proudly woven in North America supporting our local communities.

Sustainability

BIODEGRADABLE* CLEAN IMPACT TEXTILES[®]
address the daunting problem of how to deal with polyester fabric at the end of its useful life.

Biodegradable* in landfill after 1,278 days
(tested under ASTM D5511)

*Rate and extent of biodegradation into elements found in nature is 91% after 1,278 days under ASTM D5511 (Anaerobic Biodegradation of Plastic Materials Under High Solids Anaerobic Digestion Conditions). The test was done with the same component (PET) polyester and biocatalyst additive. No evidence of further degradation.

Performance

	Colorfastness to light (AATCC 16.3 Option 3) Grade 4.5 min. at 40 hours
	Colorfastness to crocking (AATCC 8) Grade 4 min. dry & Grade 4 min. wet
	Breaking Strength (ASTM D5034) 265 lbf min. warp and 286 lbf min. fill
	Seam Slippage (ASTM D4034) 108 lbf min. warp and 106 lbf min. fill
	Pilling Resistance (ASTM D3511) Class 4 min.
	Flammability CA Technical Bulletin 117-2013 Section 1 NFPA 260-2013 Class I
	* Abrasion (ASTM D4157) 100,000 double rubs min. cotton duck

*Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

Certification Marks owned by the Association for Contract Textiles, Inc.

duvalttex

USA & INTERNATIONAL | T 800-544-0200
CANADA | T 418 227-9897
For samples, visit **duvalttex.com**

