

**Name**  
Amalgam


**Designer**  
Suzanne Tick

**Style No.**  
4051


**Use**  
Upholstery

**Content**  
100% Polyester


**Abrasion**  
Wyzenbeek  
105,000 double rubs\*\*




Fluid 4051-04




Aura 4051-01




Pyrite 4051-02




Medallion 4051-03




Fuse 4051-09




Magma 4051-08



Nitro 4051-07



Fluid 4051-04



Ultraviolet 4051-05



Jolt 4051-06

**Name** **Amalgam**

**Style No.** **4051**

**Designer** Suzanne Tick

**Specification**

Use: Upholstery  
Content: 100% Polyester  
Weight: 27.26 oz per linear yard  
Width: 59"  
Pattern Repeat: None  
Directional: Yes

**Finish** Acrylic Backing

**Performance**

Abrasion: ASTM D4157 Wyzenbeek 105,000 double rubs\*\*  
Breaking Strength: ASTM D5034 Warp 841 lbf, Fill 545 lbf  
Seam Slippage: ASTM D4034 Warp 56 lbf, Fill 88 lbf  
Colorfastness to Light: AATCC 16, Grade 4.5 at 40 Hours  
Colorfastness to Crocking: AATCC 8, Wet Class 5, Dry Class 4.5  
Pilling: ASTM D3511 (Brush Pill), Class 3.5

**Flame Retardancy** Cal TB 117-2013

**Maintenance** WS, Clean with either a water-based or solvent-based cleaning agent.

**Origin** Italy

Dye lots may vary slightly from samples shown. Samples shown off the bolt.



**Canada**  
877.705.LUUM  
luumtextiles.ca

**USA**  
877.705.LUUM  
luumtextiles.com

**International**  
919.464.2922  
luumtextiles.com

cdn/us/int/06-17

© Teknion 2017.  
\*,™ Trademarks of Teknion Corporation and/or its subsidiaries or licensed to it.  
\*\*Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance.  
Wyzenbeek results above 100,000 double rubs have not been shown to be a reliable indicator of increased fabric lifespan.  
\*Certification Marks owned by the Association for Contract Textiles, Inc.